

ID	Adsorbent	Production area	Particle size	Aqueous solution			Amount of adsorbent m[g]	Solution volume V[ml]	Mixing time(1) [h]	Ion concentration of the solution			Sr adsorption ratio [%]	Kd(Sr)
				Composition,etc.	pH	Filtration ○:Yes ×:No				Cs [ppm]	Sr(2) [ppm]	I(3) [ppm]		
049	Zeolite	Niki-HOKKAIDO		Ion-exchanged water + RO	5.23	○	0.1	10	24		0.09		99.37	1.6E+04
050	Zeolite	Niki-HOKKAIDO		Ion-exchanged water + RO	5.30	○	0.1	10	24		0.96		99.15	1.2E+04
051	Zeolite	Niki-HOKKAIDO		Ion-exchanged water + RO	5.40	○	0.1	10	24		11.80		99.70	3.3E+04