

ID	Adsorbent	Production area	Particle size	Aqueous solution			Amount of adsorbent m[g]	Solution volume V[mL]	Mixing time(1) [h]	Ion concentration of the solution			Sr adsorption ratio [%]	Kd(Sr)
				Composition, etc.	pH	Filtration O: Yes X: No				Cs [ppm]	Sr(2) [ppm]	I(3) [ppm]		
033	Brucite			Ion-exchanged water	5.9	x	0.3001	30	24	0	0.1	0	3.0	3.1E+00
034	Brucite			Ion-exchanged water	5.9	x	0.3000	30	24	0	1	0	3.3	3.4E+00
035	Boehmite			Ion-exchanged water	5.9	x	0.3003	30	24	0	1	0	1.3	1.4E+00
036	Boehmite			Ion-exchanged water	5.8	x	0.3002	30	24	0	10	0	1.9	2.0E+00