

ID	Adsorbent	Production area	Particle size	Aqueous solution			Ion concentration of the solution							
				Composition, etc.	pH	Filtration ○: Yes ×: No	Amount of adsorbent m[g]	Solution volume V[m]	Mixing time(1) [h]	Cs [ppm]	Sr(2) [ppm]	I(3) [ppm]	Cs adsorption ratio [%]	Kd(Cs)
046	Zeolite	Niki-HOKKAIDO		Ion-exchanged water + RO	5.35	○	0.1	10	24	0.11			99.78	4.4E+04
047	Zeolite	Niki-HOKKAIDO		Ion-exchanged water + RO	5.42	○	0.1	10	24	1.11			99.91	1.1E+05
048	Zeolite	Niki-HOKKAIDO		Ion-exchanged water + RO	5.53	○	0.1	10	24	11.21			99.95	2.0E+05