

# Determination of Inelastic Mean Free Paths in Elemental Solids in the 200 to 5000 eV Energy Range by Absolute Elastic Peak Electron Spectroscopy

S. Tanuma, N. Okamoto, Y. Azuma, T. Kimura and K. Goto

- Introduction
- Measurement of EPI
  - Comparison of measured and calculated EPI
- IMFP determination
  - Comparison of measured and calculated IMFPs ( TPP-2M and from ELF<sub>s</sub>)
- Analysis of IMFPs determined from EPIs by Fano Plots
  - comparison of EPES with Ni-std method
- Summary

1

## 1. Introduction

- Knowledge of the values of inelastic mean free paths (IMFPs) for low-energy electrons in solids is important for quantitative surface analysis by AES, XPS, and EELS.

**: We have determined IMFPs for Ag, Au, Cr, Cu, Fe, Ga, C (Graphite) , Mo, Ni, Pt, Si, Ta, W and Zn in the 50 - 5000 eV energy range from **Absolute backscattered elastic-peak intensities** and compared with the corresponding calculated IMFPs ( optical and TPP-2M ) in order to check their reliability.**

2

# Measurements of EPIs





Figure 1. Schematic CMA system.

CMA  $\Delta E/E = 0.25\%$

Accuracy  
 $\pm 0.01\%$  (primary beam energy)  
 $\pm 0.5\%$  (Auger spectra)

Measurement of Elastic Peak Intensity



Energy range : 1 - 5,000 eV  
 ( 50 - 5,000 eV )

Instrument: Absolute Auger Spectrometer  
 -detection angle ( $42.3 \pm 6^\circ$ )


Primary beam: 1  $\mu$ A

Detector: Faraday cup

## Measured elastic peak intensity as a function of electron energy -1




# Measured elastic peak intensity as a function of electron energy -2



5

## Calculation of EPIs with MC method

$$\frac{I}{I_0} = G_w \times G_t \times f_s \int_0^\infty \left(\frac{d\eta}{dS}\right) / N_0 \exp\left(-\frac{S}{\lambda}\right) dS$$




$G_w$  : correction for window in CMA

$G_t$  : transmission efficiency of CMA

$I_0$  : incident electron current

$N_0$  : number of input electrons



**: Elastic scattering cross section**

**DHF potential**

**: Pseudo random number generator**

**Mersenne Twister**

# Measurement of transmission efficiency $G_t$




Fig. 1. (a) Virtual Sample and F.C.1 photos. (b) Schematic experimental set up.

7

## Simulation of $G_t$

Simulation results:




Fig.2. Thermal emitted electrons function for different values of  $T$ . for the acceleration of  $E_p=1\text{V}$ .






Fig.3. Energy transmission function for different values of  $\Delta E/E$ . (case for  $E_p=10\text{eV}$ )




8

# $G_t$ : Measured transmission efficiency of CMA



# Comparison of measured and calculated EPIs for Au in the 50 - 5000 eV



Measured intensity  
 - solid circles: EP current /incident

Calculated intensities from MC method (without fs correction)  
 - solid line ( optical IMFPs)  
 - dotted line ( TPP-2M)


$$\left(\frac{I^x}{I_0}\right)_{\text{cal}} = G_w \times G_t \times f_s \int_0^\infty \left(\frac{d\eta}{dS}\right)^x / N_0 \exp\left(-\frac{S}{\lambda_x}\right) dS$$

$$f_s = 1$$

200eV > : good agreement

200 eV < : large difference

# Comparison of measured and calculated EPIs of Ag, Si and Cu in the 50 - 5000 eV



11

## Determination of IMFPs from Absolute EPIs

: Measured EPI

$$\left(\frac{I^x}{I_0}\right)_{\text{measured}} : I^x \rightarrow \text{EPI} \quad I_0 = 10^{-6} \text{ A}$$

: Calculated EPI with MC (parameter  $\lambda_x$  (IMFP))

$$\left(\frac{I^x}{I_0}\right)_{\text{cal}} = G_w \times G_t \times f_s \int_0^\infty \left(\frac{d\eta}{dS}\right)^x / N_0 \exp\left(-\frac{S}{\lambda_x}\right) dS$$

: IMFP determination

$$\left| \left(\frac{I^x}{I_0}\right)_{\text{measured}} - G_w \times G_t \times f_s \int_0^\infty \left(\frac{d\eta}{dS}\right)^x / N_0 \exp\left(-\frac{S}{\lambda_x}\right) dS \right| \rightarrow \min$$

- solve above eq. for parameter  $\lambda_x$  (IMFP)


12

# Calculation of IMFPs from optical data (Optical IMFPs)

- Flow of calculation

$$\frac{d^2\sigma}{dqd\omega} = \frac{m\epsilon_0^2}{\pi N h E} \operatorname{Im} \left( \frac{-1}{\epsilon(q, \omega)} \right) \frac{1}{q}$$

$n\sigma\lambda = 1$



13

## TPP-2M

$$\lambda = \frac{E}{E_p^2 [\beta \ln(\gamma E) - CE^{-1} + DE^{-2}]} \quad (A)$$

$$\beta = -0.10 + 0.944 (E_p^2 + E_g^2)^{-0.5} + 0.069 \rho^{0.1}$$

$$\gamma = 0.19 \rho^{-0.5}$$

$$C = 1.97 - 0.9U$$

$$D = 534 - 208U$$

$$U = \frac{N_v \rho}{M} = \frac{E_p^2}{8294}$$

M: atomic weight


$\rho$ : density

$N_v$ : number of valence electrons

$E_g$ : band-gap energy


14

# IMFPs determined from Absolute EPI




15

# IMFPs determined from absolute EPI




16

# IMFPs determined from absolute EPI



17


# IMFPs determined from absolute EPI



18

# Analysis of IMFPs with Fano Plot

- We have analyzed experimentally determined IMFPs using Fano Plots which were constructed by plotting values of  $E/\lambda$  versus  $\ln E$ .



solid symbols : experimentally determined IMFPs

red solid line: fit to the energy/IMFP values with the Bethe equation

dotted line: calculated from Bethe equation (experimental IMFP value: EPES-Ni-std)

$$E/\lambda = E_p^2 \beta \ln(\gamma E) \quad \leftarrow \text{Simple Bethe equation}$$

19

## Dotted line: IMFPs from EPIs using Ni-std

- Calculation of EPI ratio to Ni-reference ; remove  $G_t$


$$f_s^x / f_s^{Ni} = 1 \quad \text{- assume that surface excitation effect is negligible for Ni-reference method.}$$

$$\left( \frac{I^x}{I^{Ni}} \right)_{cal} = \frac{\int_0^\infty (d\eta/dS)^x / N_0^x \exp(-S/\lambda_x) dS}{\int_0^\infty (d\eta/dS)^{Ni} / N_0^{Ni} \exp(-S/\lambda_{Ni}) dS}$$

Determination of IMFPs using Ni-std

- solve for parameter  $\lambda_x$  (IMFP)

$$\left[ \left( \frac{I^x}{I^{Ni}} \right)_{measured} - \left( \frac{I^x}{I^{Ni}} \right)_{cal} \right]^2 \rightarrow \min$$



Simple Bethe equation


$$E/\lambda = b + a \ln(E)$$

: Parameters were determined from curve fits


- dotted line : calculated from these parameters

20





# Analysis of IMFPs with Fano Plot(1)






# Analysis of IMFPs with Fano Plot (2)



# Analysis of IMFPs with Fano Plot(3)



# Analysis of IMFPs with Fano Plot (4)



# Results of Bethe eq. fits to measured IMFPs in the 100 - 5,000 eV range



## Average RMS deviation

Bethe fit:

- present work (from absolute EPI): 8.7 %



-EPI- Ni-ref method : 9.1%

-comparison of Bethe fit results  
: absolute EPI (present work)  
and Ni-ref EPI : 5.0 %




25

## Comparison of resulting IMFPs from the Bethe fit with optical IMFPs , TPP-2M, EPES-Ni-std (Si, W)



26

rms(%) difference of IMFPs determined present work from  
IMFPs of the Penn algorithm (optical IMFPs) and the TPP-2M



Average RMS(%): 100 - 5000 eV : 9.1 %(optical), 10.8 %(TPP-2M)

average RMS(%): 100 - 5000 eV : 11.0%(optical), 10.7%(TPP-2M)

27

## Summary

- We have carried out the experimental determinations of IMFPs for 14 elemental solids (Ag, Au, Cr, Cu, Fe, Ga, graphite, (glassy carbon,) Mo, Pt, Si, Ta, W and Zn) in the 50-5000 eV energy range from absolute backscattered elastic-peak intensities taken by a novel CMA with Monte Carlo (MC) calculations and also compared with IMFPs of the elemental solids with the Penn algorithm.

-The IMFPs determined from EPES could be fit by a simple Bethe formula in the 100 – 5000 eV energy range using Fano plot (average RMS deviation : 9%)

28

-The EPES-IMFPs of Ag, Au,Cu, Cr, glassy carbon,Ni, Pt, Si, Ta and W are in excellent agreement (RMS deviations is less than 10%; average:7% ) with those calculated from the Penn algorithm in the 100-5000 eV energy range. The average RMS deviation for 15 elemental solids is about 10%. However, the RMS deviations for Mo and graphite were large;16 and 28 % , respectively.

- Differences between the present EPES-IMFPs and IMFPs from EPES-Ni-ref method are also small (average RMS differences was 5.0 %) in the 100-5000 eV energy range.

-We may conclude that the accuracy of IMFP values for elemental solids calculated from measured ELF's are about 10% in the 100 - 5000 eV energy range.

- Surface-electronic excitation ?