



The 28th International Workshop on Rare Earth and Future Permanent Magnets and Their Applications (REPM 2025), Tsukuba, Japan, July 27-31, 2025


[O14] Theory & Simulations

Micromagnetic Simulations of Hot-deformed Nd-Fe-B Magnets Subjected to Eutectic Grain Boundary Diffusion Process






Anton Bolyachkin, Xin Tang, Nikita Kulesh, Hossein Sepehri-Amin

National Institute for Materials Science
Research Center for Magnetic and Spintronic Materials
Green Magnetic Materials Group




Wind turbines
600 kg PM / 1 MW

Hybrid & EV: 1.2 kg PM



Nd₂Fe₁₄B






● Nd ● Fe ● B

P42/mnm (136)
a = 0.8797 nm
c = 1.2226 nm


Intrinsic properties

- $\mu_0 M_s = 1.61 \text{ T}$
- $K = 4.36 \text{ MJ/m}^3$
- $\mu_0 H_a = 6.7 \text{ T}$
- $A = 8 \text{ pJ/m}$
- $T_c = 585 \text{ K}$

Grain Boundary Diffusion Process (GBDP)




Nonmagnetic Nd-rich phase



VS.


Thin ferromagnetic IGP




What is the effect of remaining grain connectivity on coercivity?

H. Sepehri-Amin *et al.* Scripta Mater. 63 (2010) 1124
 H. Sepehri-Amin *et al.* Acta Mater. 61 (2013) 6622

FIB-SEM tomography





3D Finite Element Model



Can be tuned








- 93.3 vol.% $\text{Nd}_2\text{Fe}_{14}\text{B}$ grains
- 3.9 vol.% thin IGP (3.5 nm)
- 2.8 vol.% triple junctions



Tomography-based model of sintered Nd-Fe-B magnets

14:15 - 14:30 [O15-3] Nikita Kulesh

Estimated parameters | $\mu_0 M_{\text{IGP}} = 0.8 \text{ T}$, $A_{\text{IGP}} = 2.0 \text{ pJ/m}$
 $\mu_0 M_{\text{TJ}} = 0.4 \text{ T}$, $A_{\text{TJ}} = 0.5 \text{ pJ/m}$





Grains:

$\mu_0 M_s = 1.61$ T,
 $A = 8$ pJ/m,
 $K = 4.36$ MJ/m³

Thin IGP:


M_s is varied,
 $A \propto M_s^2$,
 $K = 0$ J/m³







Experimental data


- ★ Sepehri-Amin, 2013
- Akiya, 2014
- ▲ Liu, 2016
- ◇ Seelam, 2016
- ▲ Liu, 2018
- Zhang, 2017
- Sawatski, 2018
- ◆ Xia, 2022





Note: EAs of the corresponding grains are the same throughout the models





Assumption: the chemical composition of thin IGP (and thus its M_r) doesn't change much during GBDP


- The M_r vs. H_c tradeoff of hot-deformed Nd-Fe-B magnets after the grain boundary diffusion process using a Nd-based eutectic alloy can be described by micromagnetic simulations
- Magnetization of the thin intergranular phase is estimated to be 0.9 ± 0.1 T
- Magnetostatic interaction defines the slope of M_r vs. H_c tradeoff, while exchange coupling – the bias, at high and low Nd-rich phase content, respectively

What's NEXT?

- Accounting for the core-shell structure
- **Implementing ROM** for larger models and better statistics

A. Bolyachkin *et al.*, Scripta Mater., 247 (2024) 116095

A. Bolyachkin *et al.*, npj Comp. Mat. 10 (2024) 34



Thank you for your attention!

Anton Bolyachkin, PhD
bolyachkin.anton@nims.go.jp

National Institute for Materials Science, Japan

